



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: F42B 7/04, 12/74	A1	(11) International Publication Number: WO 94/11697 (43) International Publication Date: 26 May 1994 (26.05.94)
(21) International Application Number: PCT/SE93/00950 (22) International Filing Date: 9 November 1993 (09.11.93) (30) Priority data: 9203336-4 9 November 1992 (09.11.92) SE (71)(72) Applicant and Inventor: PERSSON, Leif [SE/SE]; Häggbovägen 8, S-710 27 Dylta Bruk (SE). (74) Agents: ÖRTENBLAD, Bertile et al.; Noréns Patentbyrå, P.O. Box 27034, S-102 51 Stockholm (SE).		(81) Designated States: AU, CA, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>In English translation (filed in Swedish).</i>
(54) Title: MATERIAL FOR HUNTING AMMUNITION, AND A METHOD FOR PRODUCING SUCH MATERIAL (57) Abstract The invention is characterized in that the ammunition material comprises at least one of the materials tungsten carbide (WC) or ferrotungsten (FeW) in powder form and a material of low melting point which functions to bind the powder material to a coherent body; in that the powder material and the binder material is present in the ammunition material in such mutual proportions that the ammunition material has a density which corresponds to or is in the same order of magnitude as the density of lead. The invention also relates to a method for manufacturing the ammunition material.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TC	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Material for Hunting Ammunition, and a Method for
Producing Such Material

5 The present invention relates to hunting ammunition material. Hunting ammunition is normally produced from lead, which applies both to ball ammunition and to so-called BB-shot or pellet ammunition.

10 The use of lead, particularly lead shot or pellets, for hunting purposes is highly disadvantageous from an environmental aspect. About 700 tonnes of lead is scattered annually in this way over the countryside in Sweden alone, of which about 125 tonnes derives from shooting and hunting. About 20 tonnes of lead shot is
15 scattered in conjunction with bird shooting expeditions, this shot falling in places where the birds are liable to ingest the shot when scavenging for food, e.g. over wet-lands.

20 When using lead shot or pellets for hunting purposes, a very large quantity of lead is scattered throughout the countryside in an uncontrollable fashion, which is negative from an environmental aspect.

25 One particularly negative aspect of the use of BB lead shot to shoot birds is that the shot is scattered in a manner which results in some of the shot being eaten by the birds and causing lead poisoning. Naturally, this can lead to the death of certain birds. Moreover,
30 people who, in turn, eat birds which have eaten lead shot will also ingest a certain amount of lead.

On the other hand, lead ammunition has very good ballistic properties and also high energetic properties, in other words lead shot produces a satisfactorily high energy impulse when striking the target.
35 These properties are allied to a great extent with the specific gravity of lead, i.e. its density.

It would also seem that those weapons used for hunting purposes are designed and dimensioned for use with lead ammunition.

5 Iron ammunition in the form of iron shot is available commercially. The density of iron, however, is too low to provide the same good properties as lead, and consequently iron shot has a limited use.

10 It will be evident, however, that it would be highly beneficial to replace lead with a material whose properties correspond to those of lead in this context but in this context at the same time is harmless to the environment and ecosystem.

15 The present invention proposes a material which can be used as a substitute for lead in shot ammunition and also in ball ammunition.

20 Thus, the present invention relates to material for hunting ammunition and is characterized in that the ammunition material includes at least one of the materials tungsten carbide (WC) or ferrotungsten (FeW) in powder form, and a material of low melting point
25 which functions to bind the powder material into a coherent body; in that the powder material and the binder material is present in the ammunition material in such mutual proportions that the ammunition material has a density corresponding to or in the same order
30 of magnitude as the density of lead.

The invention also relates to a method of manufacturing such a material, this method mainly comprising the features set forth in Claim 6.

35

The invention will now be described in more detail, partly with reference to exemplifying embodiments of the invention.

The present invention thus relates to a material for the manufacture of hunting ammunition. The ammunition material comprises at least one of the materials tungsten carbide (WC) or ferrotungsten (FeW) in powder form, and a material of low melting point which functions to bind the powder material to form a coherent body.

The powder material and the binder material is present in the ammunition material in mutual proportions such that the ammunition material will have a density which corresponds to or is of the same order of magnitude as the density of lead.

Because the ammunition material has a density which corresponds to or is in the same order of magnitude as the density of lead, the ammunition will possess the same or corresponding ballistic and energetic properties as lead ammunition.

According to one preferred embodiment of the invention, the binder material is comprised of at least one of the materials zinc (Zn), tin (Sn) or aluminum (Al), which function as a sintering material. These materials have a low melting point in comparison with ferrotungsten (FeW) and tungsten carbide (WC), therewith enabling a known sintering process to be readily employed. The sintering material is preferably in powder form prior to the sintering process.

According to another preferred embodiment, the binder material is a plastic material, preferably a polyester plastic. In this case, the metallic powder material is mixed with the plastic material to obtain an homogeneous mixture. The mixture is then placed in moulds in which individual shot or balls are shaped and the plastic material then allowed to cure.

Low density and high density ammunition is already known to the art.

5 According to the present invention, both low density ammunition and high density ammunition can be produced.

10 According to one embodiment of the invention, the ammunition material of low or average density comprises tungsten carbide and zinc, preferably in about equal volumes.

15 Lead has a density of 11.3 g/cm^3 . Tungsten carbide (WC) has a density of 14.3 g/cm^3 . A mixture comprising 50 vol. % WC and 50 vol. % zinc (Zn) has a density of 10.7 g/cm^3 .

20 According to one embodiment of the invention, the high-density ammunition material comprises ferrotungsten and zinc, preferably with about 75 vol. % FeW and 25 vol. % Zn. This mixture has a density of 16.3 g/cm^3 .

25 It will be obvious that the skilled person will be able to mix the aforesaid materials or other materials in chosen proportions which will provide ammunition of the density desired, and the present invention is not therefore restricted to any particular mixture.

30 As before mentioned, the invention also relates to a method of producing said ammunition.

35 According to the invention, the ammunition material is produced by mixing at least one of the materials tungsten carbide (WC) or ferrotungsten (FeW) in powder form with a material of low melting point, melting the material of low melting point and then causing said material to solidify so as to sinter together the powder material.

5 The powder material and the sintering material are present in such mutual proportions that the ammunition material will have a density which corresponds to or is of the same order of magnitude as the density of lead.

10 The sintering process can be effected by means of suitable, well-known methods, of which one is to place the mixture in moulds for producing individual shot or balls, and to heat the moulds to sintering temperature and then allowing the moulds to cool. Subsequent to the sintering process, the shot or balls may be subjected to deformation with the intention of increasing the compactness, i.e. increasing the
15 density.

20 According to one particular method, the mixture of powder material and sintering material is, instead, subjected to a high speed moulding process so that an adiabatic process will take place where the sintering material melts.

25 By adiabatic process is meant that deformation takes place at such a high speed that the thermal energy generated in the process of deformation cannot be lead away in time, but remains essentially in the material that is deformed. In this regard, the deformation energy must also be sufficiently high to melt the sintering material to the extent desired.

30 A process of this kind can be carried out by placing the mixture in a first, open mould half for producing individual shot or balls, and then bringing a second mould half at high speed into engagement with the
35 first mould half. The first mould half shall be filled to an extent such that a coherent body in the form of a single shot or a single ball will be formed when the mould halves meet.

It will be evident from the foregoing that the present invention solves the problems mentioned in the introduction originating from the use of lead shot, since the aforesaid materials and substances do not
5 create the same environmental drawbacks as those engendered by lead.

A few materials have been mentioned in the foregoing in addition to the heavier fractions comprised of at
10 least one of the materials WC and FeW. It will be obvious in other respects that the person skilled in this art has a wide range of materials to choose from.

The present invention shall not therefore be considered restricted to the aforescribed exemplifying
15 embodiments thereof, since variations can be made within the scope of the accompanying Claims.

Claims

1. A material for hunting ammunition, c h a r -
a c t e r i z e d in that the ammunition material
5 comprises at least one of the materials tungsten
carbide (WC) or ferrotungsten (FeW) in powder form and
a material of low melting point which functions to
bind the powder material to a coherent body; and in
that the powder material and the binder material is
10 present in the ammunition material in such mutual
proportions that the ammunition material will have a
density which corresponds to or is in the same order
of magnitude as the density of lead.
- 15 2. A material according to Claim 1, c h a r a c -
t e r i z e d in that the binder material is com-
prised of at least one of the materials zinc (Zn), tin
(Sn) or aluminium (Al) which functions as a sintering
material.
- 20 3. A material according to Claim 1 or 2, c h a r -
a c t e r i z e d in that ammunition material of low
or average density comprises tungsten carbide and
zinc, preferably in about equal volumes.
- 25 4. A material according to Claim 1 or 2, c h a r -
a c t e r i z e d in that high density ammunition
material comprises ferrotungsten and zinc in propor-
tions of preferably about 75 vol. % FeW and 25 vol. %
30 Zn.
5. A material according to Claim 1, c h a r a c -
t e r i z e d in that the binder material is a plas-
tic material, preferably a polyester plastic.
- 35 6. A method for producing a material for hunting
ammunition, c h a r a c t e r i z e d in that the
ammunition material is produced by mixing at least one

of the materials tungsten carbide (WC) or ferrotungsten (FeW) in powder form with a material of low melting point, causing the material of low melting point to melt and then solidify so as to cause the last-mentioned material to sinter together the powder material; and in that the powder material and the sintering material are mixed in such mutual proportions that the ammunition material will have a density which corresponds to or is in the same order of magnitude as the density of lead.

7. A method according to Claim 6, characterized in that the sintering material is comprised of at least one of the materials zinc (Zn), tin (Sn) or aluminium (Al).

8. A method according to Claim 6 or 7, characterized by including tungsten carbide and zinc, preferably in about equal volumes in the ammunition material of low or average density.

9. A method according to Claim 6 or 7, characterized in that ferrotungsten and zinc is included in ammunition material of high density, preferably in proportions of about 75 vol. % FeW and 25 vol. % Zn.

10. A method according to Claim 6, 7, 8 or 9, characterized by subjecting the mixture of powder material and sintering material to a high speed moulding process such that an adiabatic process will occur where the sintering material melts.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00950

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: F42B 7/04, F42B 12/74

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: F42B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US, A, 4881465 (R.C. HOPPER ET AL), 21 November 1989 (21.11.89), the whole document	1-2,6-7
Y	--	5
Y	GB, A, 2200976 (WILMET LTD), 17 August 1988 (17.08.88), the whole document	5
A	GB, A, 697172 (THE BIRMINGHAM SMALL ARMS COMPANY LIMITED), 16 Sept 1953 (16.09.53), the whole document	1-10
	-- -----	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

10 February 1994

17 -02- 1994

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM

Authorized officer

Johan Löfstedt

INTERNATIONAL SEARCH REPORT
Information on patent family members

30/12/93

International application No.
PCT/SE 93/00950

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US-A-	4881465	21/11/89	NONE		
GB-A-	2200976	17/08/88	GB-A, B-	2149067	05/06/85
			US-A-	4780981	01/11/88
			US-A-	4949645	21/08/90
GB-A-	697172	16/09/53	NONE		